

Amendment

Page 3 of 3

Applicant(s): Geoffrey P. Morris et al.

Serial No.: 09/756,429 (Parent Serial No.: 09/311,909)

Filed: 8 January 2001 (Parent: 14 May 1999)

For: GLASS MICROSPHERES FOR USE IN FILMS AND PROJECTION SCREEN DISPLAYS

Remarks

Please enter and consider amended claims 1 and 10. The amendments to the claims correct typographical errors and do not add new matter.

Conclusion

The Examiner is invited to contact Applicants' Representatives at the below-listed telephone number, if there are any questions regarding this Preliminary Amendment or if prosecution of this application may be assisted thereby.

Respectfully submitted for

Geoffrey P. MORRIS et al.

By

Mueting, Raasch & Gebhardt, P.A.

P.O. Box 581415

Minneapolis, MN 55458-1415

Phone: (612)305-1220

Facsimile: (612)305-1228

Customer Number 26813

August 30, 2001
Date

By: Ann M. Mueting
Ann M. Mueting
Reg. No. 33,977
Direct Dial (612)305-1217

CERTIFICATE UNDER 37 CFR §1.8:

The undersigned hereby certifies that this paper is being deposited with the United States Postal Service as first class mail, in an envelope addressed to: Assistant Commissioner for Patents, Washington, D.C. 20231 on this 30 day of August, 2001.

By: Ann M. Mueting
Name: Ann M. Mueting



**APPENDIX A - SPECIFICATION/CLAIM AMENDMENTS
INCLUDING NOTATIONS TO INDICATE CHANGES MADE**

Serial No.: 09/756,429

Docket No.: 54789 USA 8B.008

Amendments to the following are indicated by underlining what has been added and bracketing what has been deleted.

In the Claims

For convenience, all pending claims are shown below.

1. (TWICE AMENDED) A rear projection screen comprising a plurality of glass microspheres in optical contact with a substrate and embedded in an opaque matrix; wherein the glass microspheres:
 - have an average index of refraction of [no greater than] about 1.50 to about 1.70;
 - comprise, on a theoretical oxide basis based on the amount of starting materials: greater than about 5 wt-% total of an alkali metal oxide selected from the group of Na₂O, K₂O, Li₂O, and combinations thereof;
 - no greater than about 40 wt-% SiO₂; and
 - no less than about 10 wt-% TiO₂; andas produced have less than about 15% defects in a population, and include less than the total amount of alkali metal oxide than the theoretical amount based on the amount of starting materials.

10. (TWICE AMENDED) A film comprising a plurality of glass microspheres disposed on a substrate and embedded in an opaque matrix; wherein the glass microspheres:
 - have an average index of [no greater than] about 1.50 to 1.70;
 - comprise, on a theoretical oxide basis based on the amount of starting materials: greater than about 5 wt-% total of an alkali metal oxide selected from the group of Na₂O, K₂O, Li₂O, and combinations thereof, with the proviso that Li₂O is present;
 - no greater than about 40 wt-% SiO₂; and

RECEIVED
SEP - 7 2001
C 2000 MAIL ROOM

no less than about 10 wt-% TiO_2 ; and

as produced, have less than about 15% defects in a population, and included less than the total amount of alkali metal oxide than the theoretical amount based on the amount of starting materials.